WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification	n 6 :
G02F 1/1335, 9/35	٠

(11) International Publication Number:

WO 97/44702

A1

(43) International Publication Date: 27 November 1997 (27.11.97)

(21) International Application Number:

PCT/IB97/00457

(22) International Filing Date:

30 April 1997 (30.04.97)

(30) Priority Data:

96201394.2 17 May 1996 (17.05.96) (34) Countries for which the regional or international application was filed: NL et al.

96202718.1 30 September 1996 (30.09.96) EP

(34) Countries for which the regional or international application was filed:

NL et al.

ΕP

(71) Applicant: PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).

(71) Applicant (for SE only): PHILIPS NORDEN AB [SE/SE]; Kottbygatan 7, Kista, S-164 85 Stockholm (SE).

(72) Inventors: VAN DE WITTE, Peter; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). VAN HAAREN, Johannes, Albertus, Matthijs, Maria; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). BROER, Dirk, Jan; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). STALLINGA, Sjoerd; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).

(74) Agent: RAAP, Adriaan, Y.; Internationaal Octrooibureau B.V., P.O. Box 220, NL-5600 AE Eindhoven (NL).


(81) Designated States: JP, KR, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: COMPENSATOR, LIQUID-CRYSTAL DISPLAY DEVICE AND RETARDATION FOIL



(57) Abstract

A compensator (for example, for a liquid-crystal display device) comprising a retardation foil with a tilted optical main axis and, in addition, a second optically active layer, can be manufactured in a simple mariner by providing the retardation foil and the second layer on different sides of a transparent support.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	1.1	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
ΑÜ	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
ΑZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados -	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	16	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	1L	Israel	MR	Mauritania	ÚĞ	Uganda
BY	Belarus	18	Iceland	MW	Melawi	US	United States of Americ
CA	Салада	. IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JР	Japan	NE	Niger	VN	Viet Nam
CG	Congo ·	KE	Kenya	NI.	Netherlands	YU	Yugoslavia
CII	Switzerland	KG	Kyrgyzstan	NO	No. way	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	Ne v Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ.	Kazakstan	RO	Romania	_	
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	- LI	Liechtenstein	SĐ	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Sir. gapore		

WO 97/44702 1 PCT/IB97/00457

Compensator, liquid-crystal display device and retardation foil.

The invention relates to a compensator comprising a retardation foil at least one optical main axis of which is tilted relative to the normal to a surface of the retardation foil.

A tilted optical main axis is to be understood to mean in this context that the optical main axis makes an angle α , where $0^{\circ} < \alpha < 90^{\circ}$, with the normal to the surface of the retardation foil.

The invention further relates to a liquid-crystal display device comprising such a compensator and a retardation foil as well as to a method of manufacturing a retardation foil.

A retardation foil is to be understood to mean in this context a layer which may or may not be self-supporting and which is made of a birefringent material, or a layer having an optically compensating or delaying effect (an optically anisotropic layer). In the case of birefringence, the refractive index varies as a function of the direction of the vector of the electric field, which direction is associated with a light ray. Birefringent material has only one axis for which applies that a light ray whose vector of the electric field extends along said axis is refracted with an extraordinary refractive index n.. Said axis is also referred to as the optical main axis of the material. In the case of light rays whose vector of the electric field extends perpendicularly to this axis, the refractive index may be the same in all directions (ordinary refractive index n_o). If, at right angles to this axis, the refractive index varies, then the material is referred to as biaxial material. In this application, "the optical main axis of a layer (foil)" is to be understood to mean the average optical main axis across the thickness of the layer (the foil). Dependent upon the type of material and the structure of the layer, the optical main axis of the material may vary, for example, only in a plane at right angles to the layer. The variation occurs, for example, in the angle which the optical main axis makes with the plane of the layer, so that the effective refractive index varies across the thickness of said layer. Viewed at right angles to the layer, it is also possible, however, that the direction of the optical main axis varies in the plane of the layer. In the former case, complete extinction can be brought about between polarizers crossing each other at 90 degrees; in the latter case, there is always some residual transmission.

10

15

20

5

10

15

25

30

The display devices are generally used, for example, in monitors, TV applications and, for example, display devices in motorcars and for measuring instruments. The compensators can also be used in polarizing beam splitters or in laser-optical systems for optical recording.

A compensator of the type mentioned in the opening paragraph is described in PCT application WO 96/06380 (PHN 15.171 or US appl. no. 8,516,904). In said compensator use is made of an optically anisotropic layer of a cholesterically ordered polymeric material in order to counteract grey-scale inversion in a twisted nematic display device. The polymeric material is ordered in such a manner that a molecular helix can be distinguished, the axis of the helix making an angle with a surface and with the normal to one of the substrates.

In said Patent Application, the possibility of successively arranging a plurality of anisotropic layers having different properties is suggested. A problem which may occur in such a structure is that different anisotropic layers influence each other via the interface. In addition, the manufacture of such an assembly of anisotropic layers is complex because a layer cannot be provided until after the preceding layer has cured.

It is an object of the invention to obviate one or more of said disadvantages. The invention further aims at providing a compensator which can be used, inter alia, in liquid-crystal display devices.

To this end, a compensator in accordance with the invention is characterized in that the compensator comprises a second retardation foil, with the retardation foils being provided on either side of a light-transmitting support.

The retardation foils can be made of inorganic or organic material.

As the light-transmitting support (substrate) is situated between the retardation foils (optically anisotropic layers), the optical properties of each individual retardation foil can be set completely independently of the other retardation foils, in particular, if also the second retardation foil has at least one optical main axis which is tilted relative to the surface and the normal to the surface of the second retardation foil. This is advantageous, in particular, if a preferred direction of the optical main axis is imposed on the anisotropic layers via an aligning effect of the support (for example rubbing or the use of a pre-tilt layer), because such an aligning effect may extend, for example, in the case of anisotropic layers of polymerized liquid-crystalline material, over a plurality of monolayers of this material. The aligning force of the support acting on the monolayers of the first retardation foil may then also have an effect on the monolayers of a second retardation foil

via the monolayers of the first retardation foil. By virtue thereof, the influence of an aligning force acting on the first monolayers of a second retardation foil can be influenced in an unfavorable manner. Also if one of the retardation foils has an optical main axis which is not tilted relative to the surface and the normal to the surface of the relevant retardation foil, it is advantageous to provide the retardation foils on either side of the support, because, for example, both sides can be rubbed beforehand and at the same time.

A preferred embodiment of the compensator in accordance with the invention is characterized in that, viewed at right angles to the support, the optical main axes of the retardation foils cross each other.

The support comprising two retardation foils can be manufactured in a simple manner by first introducing the desired aligning effect on both sides (whether or not simultaneously) (for example by rubbing in two different, preferably, mutually perpendicular directions or, in specific applications, parallel directions) and subsequently moistening both sides by means of a suitable material for the retardation foil.

A further preferred embodiment of a compensator in accordance with the invention is characterized in that the retardation foils predominantly comprise polymerized, nematic liquid-crystalline material, the liquid-crystal molecules in the polymerized liquid-crystalline material being oriented parallel to an optical main axis and exhibiting a tilt angle relative to the support (the substrate).

By virtue thereof, the directions of orientation of the liquid-crystal molecules in the polymerized liquid-crystalline material in the retardation foils are substantially constant.

In this context, the direction of orientation of a liquid-crystal molecule is to be understood to mean the perpendicular projection of the director of the liquid-crystal molecule on the support (the substrate).

The liquid-crystalline material may be partly polymerized, but, preferably, it is polymerized substantially completely.

Dependent upon the method of manufacture, the liquid-crystal molecules in the polymerized or vitrified nematic, liquid-crystalline material have a tilt angle relative to the substrates, which varies (for example by using surface-active substances) or which is substantially constant. This can be determined by means of conoscopy or microscopy using polarized light (polarizing microscopy).

A preferred embodiment of a compensator in accordance with the invention is characterized in that the direction of orientation of the liquid-crystal molecules in

10

15

25

the polymerized liquid-crystalline material in at least one of the retardation foils is substantially constant.

During the manufacture of a retardation foil, the tilt angle of the liquidcrystal molecules (director profile) can be obtained by using a polymeric material which is formed from a liquid-crystal monomer.

In principle, all liquid-crystalline polymeric materials can be used as the material for the retardation foils. However, use is preferably made of liquid-crystalline polymeric materials which are the reaction product of monomers or of a mixture of monomers comprising a reactive group. Such polymeric materials have the advantage that the liquid-crystalline groups can be oriented prior to polymerization. Polymerization causes such an orientation to be frozen as it were. It is noted that such a mixture may additionally comprise non-reactive (liquid-crystalline) materials and/or non-liquid-crystalline monomers. The reactive monomers preferably comprise a liquid-crystalline group.

For the reactive group use can be made of vinyl ethers, thiolene systems or epoxy groups. However, use is preferably made of reactive groups in the form of (meth)acrylate groups. Monomers comprising a(n) (meth)acrylate group proved to be excellently processable. In principle, the monomers can be thermally polymerized. In practice, radical-polymerization under the influence of actinic radiation, in particular UV light, is the best way of polymerizing the monomers. This has the advantage that persons skilled in the art can choose the temperature at which the mixture should be polymerized themselves. The choice of the temperature often is very important as the liquid-crystalline properties of the mixture to be polymerized are governed to a substantial degree by the temperature.

Preferably, the mixture to be polymerized also comprises monomers having two or more reactive groups of the above-mentioned type. During polymerization, the presence of such monomers leads to the formation of a three-dimensional network. This causes the optical properties of the inventive retardation foil to become less sensitive to variations in temperature. In particular for foils which are employed at different temperatures, such a small temperature-dependence of the optical properties is very favorable.

Liquid-crystalline molecules which can be used within the scope of the invention correspond to the general formula

$$A-B-M-(B)-(A)$$

In this formula, M represents a group whose chemical structure and rigid conformation cause the molecule to become highly anisotropic. Suitable M groups are disclosed, inter alia, in

5

10

15

20

25

WO 97/44702 5 PCT/IB97/00457

USP 4,398,803 and WO 95/24454. B represents a so-called spacer group. Dependent upon the desired properties, the monomers used comprise one or two spacer groups. Spacer groups are also known from the above-mentioned Patent publications. A represents a reactive group of the above-mentioned type. The liquid-crystalline molecules may comprise one or two reactive groups. As stated above, a part of the liquid-crystalline molecules in the mixture may be non-reactive. In that case, these molecules do not comprise A-type groups.

A preferred embodiment of the display device is characterized in that the polymerized material comprises liquid-crystalline molecules which are provided, at one end, with a non-polar group and, at the other end, with a polar group. The presence of this type of liquid-crystal molecules causes the liquid-crystalline material of the mixture to be polymerized to assume the homeotropic phase at a short distance from the substrate. As a result, the desired ordering of the tilt in the liquid-crystalline material of the retardation foil takes place almost spontaneously. Consequently, in this case treatments with electric fields to induce said tilt are redundant. This simplifies the manufacture of such foils.

Liquid-crystalline molecules having a polar end and a non-polar end correspond to the general formula

R-B-M-Z

where B and M have the above-mentioned meaning. In this case, the spacer group B serves as the non-polar group of the molecule and Z represents a polar group, such as -CN, -OH, -NO₂, -COOH or -C(O)O-CH₃, but also phosphates, phosphonates and sulphonates are possible. R represents a further substituent.

. ...

75

A further preferred embodiment of the display device is characterized in that at the end provided with the non-polar group, the liquid-crystal molecules are covalently bonded to the polymerized material. This is achieved if for R use is made of a reactive group of the above-mentioned type. By virtue of this measure, the optical properties of the inventive retardation foil become less sensitive to variations in temperature. In particular for foils which are employed at different temperatures, such a small temperature-dependence of the optical properties is very favorable. By virtue of said measure, the foils can also incidentally withstand (for example during storage or transport, or in automotive applications) very high temperatures without the molecular order being lost.

The tilt may be substantially uniform. Alternatively, during the manufacture of the display device, a pretilt can be induced in one or both boundary surfaces, for example by means of the method described in USP 5,155,610. Dependent upon this pretilt, the optically anisotropic layer may have, for example, a combined "splay and bend"

10

15

20

25

deformation. During the manufacture, it is also possible to influence the eventual director profile by means of electric and/or magnetic fields. This may result, for example, in a preferred direction for the directors. Such a preferred direction can alternatively be attained during polymerization in the smectic C-phase of liquid-crystalline materials.

Preferably, a compensator (support provided with retardation foils) is manufactured as an integral body and then combined with the display device. Alternatively, however, the retardation foils may be individually provided. A preferred embodiment of such a retardation foil is characterized in that the liquid-crystalline material comprises liquid-crystal molecules which, at the location of the support, are oriented substantially parallel to the support or at a small angle relative to the support, and, at a free surface of the liquid-crystalline material, predominantly at right angles to said free surface (so-called homeotropic orientation).

Dependent upon the thickness of the layer, a substantially homeotropic orientation at the surface is achieved in said layer; in practice, the tilt angle at the surface of the layers is smaller than 90° for the majority of the liquid-crystal molecules.

The homeotropic orientation causes the molecules to exert an aligning force on a layer to be provided next, so that the preferred orientation of molecules in this layer is, for example, initially homeotropic. In this case, however, any horizontal, aligning force which is introduced, for example, by mechanical shearing is not influenced by the underlying layer.

Thus, a further compensator in accordance with the invention is characterized in that the first layer (of said retardation foil) is provided with a second layer comprising completely or partly polymerized or vitrified liquid-crystalline material which contains liquid-crystal molecules which, at the location of the first layer, are oriented predominantly at right angles to the support and, at the location of the free surface of the material of the second layer, predominantly parallel to the surface of the second layer. In a variant, the first layer is provided with a second layer comprising completely or partly polymerized or vitrified liquid-crystalline material which contains liquid-crystal molecules which, at the location of the first layer, are oriented predominantly at right angles to the support and, at the surface of the second layer, predominantly parallel to the free surface of the material of the second layer.

These and other aspects of the invention will be apparent from and elucidated with reference to the embodiments described hereinafter.

5

10

15

20

invention,

In the drawings:

Fig. 1 is a schematic, cross-sectional view of a part of a liquid-crystal display device in accordance with the invention,

Figs. 2, 3 and 4 schematically show compensators in accordance with the

Figs. 5, 6 and 7 show variants of the compensator of Fig. 2,

Fig. 8 shows another compensator in accordance with the invention,

Fig. 9 shows the structural formulas of a number of materials used, and

Fig. 10 shows yet another compensator in accordance with the invention.

10

15

20

25

30

5

Fig. 1 is a schematic, cross-sectional view of a part of a liquid-crystal display device comprising a liquid-crystal cell 1 with, in this example, a twisted nematic, liquid-crystalline material 2 sandwiched between two substrates 3, 4, for example, of glass, which are provided with electrodes 5, 6. The device further comprises two polarizers 7, 8 whose directions of polarization cross each other at right angles. The cell further includes orientation layers (not shown), which orient the liquid-crystalline material on the inner surfaces of the substrates, in this example, in the direction of the polarization axes of the polarizers, so that the cell has a twist angle of 90 degrees. In this case, the liquid-crystalline material has a positive optical anisotropy and a positive dielectric anisotropy. Thus, if a voltage is applied to the electrodes 5, 6, the molecules and hence the directors are oriented in accordance with the field. Therefore, in an ideal case, all molecules extend substantially perpendicularly to both substrates. In practice, however, this situation requires too high a voltage; at customary voltages, the molecules make a small angle with the normal to the substrates 3, 4. As a result, at specific angles, the viewer looks practically in the direction of the molecules and, at other angles, the viewer looks rather at right angles to the molecules, so that light which is still passed at this voltage, is subject to a substantial and, in addition, asymmetric angle-dependence. This angle-dependence can be reduced by means of a compensator formed of one or more retardation foils, in this example two retardation foils 9, 9b, which predominantly comprise polymerized liquid-crystalline material containing liquidcrystal molecules having a tilt angle relative to the substrates, with the average directions of orientation of the liquid-crystal molecules in both retardation foils, viewed at right angles to the substrates, making an angle of 90 degrees with each other. The polymerized liquidcrystal molecules of the retardation foil 9 extend, in this example, parallel to the direction of polarization of polarizer 8 and have an average tilt angle of 30 degrees. In this example, the polymerized liquid-crystal molecules of the retardation foil 9^b extend parallel to the direction

WO 97/44702 PCT/IB97/00457 8

of polarization of polarizer 9 and also have an average tilt angle of 30 degrees.

On the one hand, the average tilt angle in the retardation foils 9°, 9° is preferably larger than 5 degrees because smaller angles hardly lead to an improvement of the grey-scale inversion and angle-dependence. On the other hand, this tilt angle should preferably not exceed 70 degrees because, otherwise, the retardation foils acquire too much axial symmetry as a function of the viewing angle. The best results are achieved at values ranging between 10 degrees and 40 degrees.

The retardation foils can be manufactured, for example, by providing both sides of a supporting plate or substrate 10 with orienting layers 11, for example, polyimide 10 rubbed in anti-parallel directions or polyvinyl alcohol, so that a high tilt is attained. Instead of rubbed polyimide, use can alternatively be made of a suitable, linearly polarized photosensitive material (for example a photopolymer such as poly(vinyl 4-methoxy-cinnamate) to align the liquid-crystal molecules. However, use is preferably made of a substrate 10 of a single layer of triacetate cellulose on which, if necessary, an aligning layer (orientation layer) 11 of polyvinyl alcohol is provided, which substrate is rubbed in mutually perpendicular directions on both sides.

The liquid-crystalline material provided on the substrate thus prepared comprises liquid-crystal molecules which, at the location of the substrate, adopt the aligning effect of the substrate (produced by rubbing or otherwise in an orientation layer 11) and are 20 oriented, at a free surface, in a direction which is predominantly perpendicular to said surface (homeotropic alignment). As a result, the orientation of the molecules at the substrate will be substantially planar or with a small tilt angle (indicated in Fig. 2 by the directors 12 in retardation foil 9^a). In a subsequent layer, the aligning influence of the orientation layer will be slightly reduced, so that this layer contains more homeotropically aligning molecules and the average tilt angle of the directors 12' is slightly larger. The orientation of the molecules at the surface is substantially exclusively homeotropic (directors 12"). Also in retardation foil 9b, the average tilt angle through the foil increases from almost zero degrees at the orientation surface to a specific magnitude (up to 90 degrees, depending on the thickness of the foil) at the free surface. However, an average tilt angle of 90 degrees is not absolutely necessary.

If necessary, the retardation foil 9^b may also be in the form of a retardation filter whose main axis is not tilted.

A suitable mixture for the liquid-crystalline material comprises 40 wt. % of a reaction LC material (a mixture of 25 wt. % 296 (see a, Fig. 9) and 75 wt. % 716 (see b,

WO 97/44702 9 PCT/IB97/00457

Fig. 9)) and 60% of a non-reactive cyanobiphenyl mixture. This mixture was provided by immersing the entire substrate or by spinning it onto the rubbed surfaces, whereafter it was polymerized by means of UV radiation in a nitrogen atmosphere or vitrified. As, on the one hand, the molecules are oriented with a small tilt angle at the supporting surface, and, on the other hand, more molecules are aligned substantially homeotropically at the free surface, an average tilt angle α is obtained (Fig. 2). A similar structure is attained with molecules which assume a homeotropic alignment at the substrate and a planar alignment at the surface. This can alternatively be achieved by means of other methods (provision by means of a doctor blade) and substrates (directly onto glass). Another mixture, which did not comprise non-reactive liquid-crystalline material, so that the strength of the layer was increased, was composed of 25 wt.% 296 (see a, Fig. 9) and 75 wt.% 76 (see c, Fig. 9).

The compensator 9 is formed by providing both sides of the substrate with two such retardation foils having varying tilt angles.

A modification in which both retardation foils are situated on one side of the substrate is shown in Fig. 3. As, in this example, the molecules 12" of the retardation foil 9° are homeotropically aligned at the interface between the retardation foils 9° and 9°, the homeotropic alignment can be induced in a simple manner in the retardation foil 9° which is situated above the retardation foil 9°. If the mixture contains sufficient molecules which tend to assume a planar orientation, then the tilt angle decreases again, so that an average angle of approximately 25 degrees is formed. The preferred direction in the retardation foil 9° is introduced, for example, by mechanical shearing or by covering the entire compensator, during the polymerization operation, with a thin layer (film) provided with an orienting layer.

In the retardation foil shown in Fig. 4, the tilt angle in foil 9^b at the interface between the retardation foils 9^a and 9^b is made substantially parallel to the interface by means of a rubbing treatment. A thin, transparent, optically isotropic protective layer 15 is provided in order not to disturb the underlying perpendicular alignment.

The directions of orientation, as shown in Fig. 2 for the layers 9 (combined splay and bend configuration), in which the tilt angle at the free surface may also be smaller than 90 degrees can also be obtained by using a liquid-crystalline starting material which spontaneously adopts such a configuration because the ratio K_{11}/W between the elastic constant K_{11} and the (polar) anchoring energy coefficient W is chosen to be smaller than 300 nm.

After a substrate has been oriented, it is coated, using one of the methods

10

15

20

25

described hereinabove, with the liquid-crystalline material, whereafter a polymerization step is carried out.

Fig. 5 shows a variant of the compensator shown in Fig. 2, in which the retardation foils 9⁴, 9⁶ comprise sub-layers 19, 19', 19" and 19'". In this case, the tilt angles in each one of the sub-layers 19 are substantially the same. As regards retardation foil 9⁴, the directions of orientation of the associated molecules (indicated by means of directors 12, 12', 12" and 12'") and hence the optical main axes extend, in this example, in the plane of the drawing and, as regards retardation foil 9⁶, in a plane perpendicular to the plane of the drawing. The optical main axis of the retardation foil 9⁶ may alternatively extend in another suitable plane which is unequal to the plane of the drawing.

In the device shown in Fig. 6, the directions of orientation of the associated molecules (indicated by means of directors 12, 12', 12" and 12'") in successive sub-layers 19, 19', 19", 19'" of the retardation foil 9° make a small angle with each other. As a result, the optical main axis of the retardation foil 9° extends in a plane which makes an angle with the plane of the drawing. In the same manner, the directions of orientation of the associated molecules (indicated by means of directors 12, 12', 12" and 12'") in successive sub-layers 19, 19', 19", 19'" of the retardation foil 9° make a small angle with each other. As a result, the optical main axis of the retardation foil 9° extends in a plane which makes an angle with the plane at right angles to the plane of the drawing. Both optical main axes cross each other, for example, at an angle ranging between 60 and 120 degrees.

In the device shown in Fig. 6, the directions of orientation of the molecules in successive sub-layers 19 are different at the boundary between two sub-layers, whereas they are substantially equal in the device shown in Fig. 7. Nevertheless, the direction of orientation of director 12' in retardation foil 9° differs from that of director 12 due to the fact that a small quantity of a chiral component is added to the mixture of liquid-crystalline materials to be polymerized or vitrified. The polymerized (vitrified) sub-layer 19 serves as the orientation layer for the sub-layer 19' in a subsequent process step. If necessary, the material of the sub-layer 19' may again contain a small quantity of a chiral component. The relevant chiral component may have the same chirality, so that the angle which the optical main axis of the complete retardation foil makes with the plane of the drawing is increased with respect to the angle which the optical main axis of the sublayer 19 makes with the plane of the drawing. In the case of an opposite chirality, the angle which optical main axis of the retardation foil makes with the plane of the drawing is reduced; dependent upon the quantity of the chiral component and the thickness of the sub-layer 19',

5

10

15

20

25

WO 97/44702 PCT/IB97/00457 11

the optical main axis of the complete retardation foil may again extend in the plane of the drawing. Of course, many intermediate forms are also possible.

Fig. 8 shows a compensator 9 comprising a transparent support 9 and retardation foils 9^a, 9^b on the two different sides of the support 10, the optical main axes of 5 said retardation foils making an angle (for example α) with the support and cross each other (for example at right angles). The retardation foils 9°, 9° can be obtained by obliquely vapordepositing a suitable material, such as tantalum oxide or tungsten oxide. As, in this case, the direction of the optical main axis is determined exclusively by the direction of deposition, the retardation foils can be so provided on both sides of substrate 10 that they include an angle between the optical main axes. It is alternatively possible to use sub-layers in a manner similar to that shown in the example of Fig. 3. Other suitable materials are silicon oxide or titanium oxide. Said materials may be provided, for example, on a transparent saw-tooth structure.

Although, in the above examples, the retardation foils 9^a, 9^b on the two different sides of the support 10 have such a structure that the optical axis of the retardation foil is tilted relative to the normal to the surface of the retardation foil, one of the two retardation foils may alternatively be constructed as a uniaxial foil, for example, having an optical main axis extending parallel to the support. A possible example is shown in Fig. 10. A retardation foil 9^a is provided on one side of the support 10, whereas, on the other side, a uniaxial foil 9° is provided.

In summary, the invention relates to a compensator (for example, for a liquid-crystal display device), which compensator comprises a retardation foil having a tilted optical main axis and, in addition, a second optically active layer, which are provided on different sides of a transparent support, which enables the manufacture to be simplified.

10

15

CLAIMS:


- 1. A compensator comprising a retardation foil at least one optical main axis of which is tilted relative to the normal to a surface of the retardation foil, characterized in that the compensator comprises a second retardation foil, with the retardation foils being provided on either side of a light-transmitting support.
- A compensator as claimed in Claim 1, characterized in that the second retardation foil has at least one optical main axis which is tilted relative to the normal to a surface of the second retardation foil.
 - 3. A compensator as claimed in Claim 1, characterized in that the second retardation foil is a uniaxial foil whose optical main axis extends parallel to the surface of the support.
 - 4. A compensator as claimed in Claim 2, characterized in that, viewed at right angles to the support, the optical main axes of the retardation foils cross each other substantially at right angles.
- 5. A compensator as claimed in any one of Claims 1 to 4, characterized in that at least one retardation foil predominantly comprises polymerized or vitrified, nematic liquid-crystalline material, the liquid-crystal molecules in the polymerized or vitrified liquid-crystalline material being oriented parallel to the optical main axis and exhibiting a tilt angle relative to a surface of the support.
- 6. A compensator as claimed in Claim 5, characterized in that the size of the tilt angles in the retardation foils, viewed from the common support, increases from the surfaces of the support.
 - 7. A compensator as claimed in Claim 5 or 6, characterized in that the tilt angles of the liquid-crystal molecules in the polymerized or vitrified, nematic liquid-crystalline material in at least one of the retardation foils increase or decrease, viewed at right angles to the retardation foil.
 - 8. A compensator as claimed in any one of Claims 5 to 7, characterized in that the tilt angles of the liquid-crystal molecules in the polymerized or vitrified, nematic liquid-crystalline material in a retardation foil have a substantially constant value.
 - 9. A compensator as claimed in Claim 8, characterized in that the tilt angles

25

of the liquid-crystal molecules in the polymerized or vitrified, nematic liquid-crystalline material in the retardation foil range between at least 5 degrees and maximally 70 degrees.

- 10. A compensator as claimed in Claim 9, characterized in that the tilt angles of the liquid-crystal molecules in the polymerized or vitrified, nematic liquid-crystalline material in the retardation foil range between at least 10 degrees and maximally 40 degrees.
- 11. A compensator as claimed in any one of Claims 5 to 10, characterized in that the liquid-crystalline material comprises liquid-crystal molecules which, at the location of the support, are oriented predominantly parallel to the support or at a small angle relative to the support, and at a free surface of the liquid-crystalline material, predominantly at right angles to said free surface.
 - 12. A compensator as claimed in any one of Claims 5 to 10, characterized in that the liquid-crystalline material comprises liquid-crystal molecules which, at the location of the support, are oriented predominantly at right angles to the support and, at a free surface of the liquid-crystalline material, parallel to the surface or at a small angle relative to said surface.
 - 13. A compensator as claimed in any one of Claims 5 to 10, characterized in that the nematically polymerized or vitrified material comprises liquid-crystal molecules which are provided, at one end, with a non-polar group, and, at the other end, with a polar group.
- 20 14. A compensator as claimed in any one of Claims 1 to 4, characterized in that at least one retardation foil comprises a material of the group formed by tantalum oxide, tungsten oxide, silicon oxide and titanium oxide.
 - A retardation foil comprising a transparent support on which a first layer containing completely or partly polymerized or vitrified nematic, liquid-crystalline material is situated, characterized in that the liquid-crystalline material contains liquid-crystal molecules which, at the location of the support, are oriented substantially parallel to the support or at a small angle relative to the support, and, at a free surface of the liquid-crystalline material, substantially at right angles to the free surface.
- 16. A retardation foil comprising a transparent support on which a first layer containing completely or partly polymerized or vitrified nematic, liquid-crystalline material is situated, characterized in that the liquid-crystalline material contains liquid-crystal molecules which, at the location of the support, are oriented substantially at right angles to the support and, at a free surface of the liquid-crystalline material, parallel to the surface or at a small angle relative to the surface.

- 17. A retardation foil comprising a transparent support on which a layer of a birefringent material is situated, characterized in that the retardation foil comprises a plurality of sub-layers.
- 18. A retardation foil as claimed in Claim 17, characterized in that at least one sub-layer predominantly comprises polymerized or vitrified nematic, liquid-crystalline material, the liquid-crystal molecules in the polymerized or vitrified liquid-crystalline material being oriented parallel to the optical main axis and exhibiting a tilt angle relative to a surface of the support.
- 19. A retardation foil as claimed in Claim 18, characterized in that at least one sub-layer comprises a material of the group formed by tantalum oxide, tungsten oxide, silicon oxide and titanium oxide.
 - 20. A compensator as claimed in any one of Claims 1 to 3, comprising at least one retardation foil as claimed in any one of Claims 15 to 19.
- A liquid-crystal display device having a display cell, which comprises a layer of a liquid-crystalline material between two substantially parallel substrates, and a first and a second polarizer, characterized in that the liquid-crystal display device comprises a retardation foil as claimed in any one of Claims 15 to 19.
 - A liquid-crystal display device having a display cell, which comprises a layer of a nematic, liquid-crystalline material between two substantially parallel substrates, and a first and a second polarizer, characterized in that the liquid-crystal display device comprises a compensator as claimed in any one of Claims 1 to 14 or 20.
- A method of manufacturing a retardation foil, in which a liquid-crystalline material is provided on an oriented surface of a substrate and then polymerized or vitrified, characterized in that the ratio K₁₁/W between the elastic constant K₁₁ of the liquid-crystalline material and the (polar) anchoring-energy coefficient W between the substrate and the liquid-crystalline material is smaller than 300 nm.



F1G.1




FIG. 2




FIG.3




FIG.4





FIG.5



4/5





FIG.7






FIG.10

$$H_{2}C = CH - C - 0 - (CH_{2})_{11} - 0 - C - C - 0 - (CH_{2})_{11} - 0 - C - HC = CH_{2}$$

a

h

$$H_2 C = CH = \overset{0}{C} = 0 (CH_2)_6 - 0$$

C

FIG.9

International application No.

PCT/IB 97/00457

A. CLASSIFICATION OF SUBJECT MATTER IPC6: G02F 1/1335, G02F 9/35 According to International Patent Classification (IPC) or to both national classification and IPC B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC6: G02F Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched SE,DK,FI,NO classes as above Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) WPI, CLAIMS C. DOCUMENTS CONSIDERED TO BE RELEVANT Citation of document, with indication, where appropriate, of the relevant passages Category* Relevant to claim No. Х US 5237438 A (T. MIYASHITA ET AL.), 17 August 1993 (17.08.93), column 12, line 25 - column 14, 1-4.14line 13, figure 7, abstract EP 0678567 A1 (SUMITOMO CHEMICAL COMPANY, LIMITED), X 17,23 25 October 1995 (25.10.95), abstract US 5359443 A (T. TOYOOKA ET AL.), 25 October 1994 Α 1-23 (25.10.94), abstract US 4984874 A (T. YAMAMOTO ET AL.), 15 January 1991 (15.01.91), column 5, line 59 - column 6, line 59, Α 1-23 figure 1, abstract Further documents are listed in the continuation of Box C. See patent family annex. Special categories of cited documents: later document published after the international filing date or priority document defining the general state of the art which is not considered date and not in conflict with the application but cited to understand to he of particular relevance the principle or theory underlying the invention erlier document but published on or after the international filing date "X" document of particular relevance: the claimed invention cannot be document which may throw doubts on priority claim(s) or which is considered novel or cannot be considered to involve an inventive step when the document is taken alone cited to establish the publication date of another citation or other special reason (as specified) document of particular relevance: the claimed invention cannot be document referring to an oral disclosure, use, exhibition or other considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art means document published prior to the international filing date but later than the primity date claimed "&" document member of the same patent family Date of the actual completion of the international search Date of mailing of the international search report 2 4 - 10 - 1997 23 October 1997 Name and mailing address of the IS/.; Authorized officer Swedish Patent Office Box 5055, S-102 42 STOCKHOLIA Karin Säfsten Facsimile No. + 46 8 666 02 86 Telephone No. + 46 8 782 25 00

Form PCT/ISA/210 (second sheet) (July 1992)

International application No.

PCT/IB 97/00457

Box 1 Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)	
This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following re-	330UZ:
1. Claims Nos.: because they relate to subject matter not required to be searched by this Authority, namely:	
2. Claims Nos.: because they relate to parts of the international application that do not comply with the prescribed requirements to an extent that no meaningful international search can be carried out, specifically:	such
3. Claims Nos.: because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.	.4(a).
Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)	
This International Searching Authority found multiple inventions in this international application, as follows:	
See next sheet!	
1. As all required additional search fees were timely paid by the applicant, this international search report cover searchable claims.	s all
2. X As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payr of any additional fee.	וחפם
3. As only some of the required additional search fees were timely paid by the applicant, this international search recovers only those claims for which fees were paid, specifically claims Nos.:	port
4. No required additional search fees were timely paid by the applicant. Consequently, this international search reported to the invention first mentioned in the claims; it is covered by claims Nos.:	ort is
Remark on Protest The additional search fees were accompanied by the applicant's protest.	
No protest accompanied the payment of additional search fees.	

Form PCT/ISA/210 (continuation of first sheet (1)) (July 15:92)

International application No. PCT/IB 97/00457

- I. Claims 1-16, 18-22 define a compensator comprising a retardation foil, a retardation foil and a liquid display device.
- II. Claim 17 defines a retardation foil.
- III. Claim 23 defines a method of manufacturing a retardation foil.

Since there is no technical relationship among these inventions involving one ore more of the same or corresponding special technical feature, as defined in Rule 13.2, the claims are considered to represent three different inventive concepts, and do therefore not comply with the requirements of unity of

Form PCT/ISA/210 (extra sheet) (July 1992)

Information on patent family members

International application No. PCT/IB 97/00457

01/10/97

Patent document cited in search report		r dividation		Patent family member(s)		
US	5237438	A	17/08/93	EP JP JP JP JP	0512459 4330416 4330417 5019251 5061037 5061038	A 18/11/92 A 18/11/92 A 29/01/93 A 12/03/93
EP	0678567	A1	25/10/95	JP US	8005839 / 5601884 /	
JS 	5359443	A	25/10/94	EP JP JP	0543678 / 5142509 / 5142510 /	11/06/93
IS	4984874	A	15/01/91	EP JP	0350075 A 2124527 A	,,

			•	
			•	
		ż		



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: (11) International Publication Number: A1 G02F 1/1335, G09F 9/35

WO 97/44702 (43) International Publication Date: 27 November 1997 (27.11.97)

PCT/IB97/00457 (21) International Application Number:

30 April 1997 (30.04.97) (22) International Filing Date:

(30) Priority Data: 17 May 1996 (17.05.96) 96201394.2 (34) Countries for which the regional or NL et al. international application was filed: 30 September 1996 (30.09.96) 96202718.1 EP

(34) Countries for which the regional or international application was filed: NL et al.

(71) Applicant: PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).

(71) Applicant (for SE only): PHILIPS NORDEN AB [SE/SE]; Kottbygatan 7, Kista, S-164 85 Stockholm (SE).

(72) Inventors: VAN DE WITTE, Peter, Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). VAN HAAREN, Johannes, Albertus, Matthijs, Maria; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). BROER, Dirk, Jan; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). STALLINGA, Sjoerd; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).

(74) Agent: RAAP, Adriaan, Y.; Internationaal Octrooibureau B.V., P.O. Box 220, NL-5600 AE Eindhoven (NL).


(81) Designated States: JP, KR, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With a revised version of the international search report.

(88) Date of publication of the revised version of the international 12 February 1998 (12.02.98) search report:

(54) Title: COMPENSATOR, LIQUID-CRYSTAL DISPLAY DEVICE AND RETARDATION FOIL



(57) Abstract

A compensator (for example, for a liquid-crystal display device) comprising a retardation foil with a tilted optical main axis and, in addition, a second optically active layer, can be manufactured in a simple manner by providing the retardation foil and the second layer on different sides of a transparent support.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	, FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IŁ	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of Americ
CA	Canada	ΙT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	- NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		



International application No. PCT/IB 97/00457

A. CLAS	SIFICATION OF SUBJECT MATTER	•	
IPC6:	GO2F 1/1335, GO9F 9/35 to International Patent Classification (IPC) or to both to	national classification and IPC	
	OS SEARCHED		
Minimum d	ocumentation searched (classification system followed	by classification symbols)	
IPC6:			
Documenta	tion searched other than minimum documentation to th	ne extent that such documents are included i	n the fields searched
SE,DK,	FI,NO classes as above		
Electronic d	ata base consulted during the international search (nam	ne of data base and, where practicable, searc	h terms used)
WPI, C	AIMS		
C. DOCU	MENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where ap	propriate, of the relevant passages	Relevant to claim No.
X	US 5237438 A (T. MIYASHITA ET A (17.08.93), column 12, line line 13, figure 7, abstract	25 - column 14,	1-4,14
	·		
х	EP 0678567 A1 (SUMITOMO CHEMICA 25 October 1995 (25.10.95),		17,23
A	US 5359443 A (T. TOYOOKA ET AL. (25.10.94), abstract), 25 October 1994	1-23
			,
A	US 4984874 A (T. YAMAMOTO ET AL (15.01.91), column 5, line figure 1, abstract	.), 15 January 1991 59 - column 6, line 59,	1-23
	<u></u>		
Furthe	er documents are listed in the continuation of Bo	x C. X See patent family annex	·
	categories of cited documents	To later document published after the inte	
to be of	nt defining the general state of the art which is not considered particular relevance	the principle or theory underlying the	invention
"L" docume	note that published on or after the international filing date on which may throw doubts on priority claim(s) or which is establish the publication date of another citation or other	"X" document of particular relevance: the considered novel or cannot be consider step when the document is taken alone	red to involve an inventive
special s "O" document means	reason (as specified) nt referring to an oral disclosure, use, exhibition or other	"Y" document of particular relevance: the considered to involve an inventive step combined with one or more other such being obvious to a person skilled in the	when the document is a document, such combination
	nt published prior to the international filing date but later than rity date claimed	"&" document member of the same patent	
Date of the	actual completion of the international search	Date of mailing of the international s	earch report
22 ೧-4 -	han 1007	11-11-1997	
	ber 1997 mailing address of the ISA/	Authorized officer	
Swedish F	Patent Office		
	S-102 42 STOCKHOLM No. +46 8 666 02 86	Karin Säfsten Telephone No. +4687822500	

International application No.

PCT/IB 97/00457

Box I Obs	ervations where certain claims were found unsearchable (Continuation of item 1 of first sheet)
1	
1 Bis internatio	nal search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons
1. Clair	ms Nos.: use they relate to subject matter not required to be searched by this Authority, namely:
becau	as Nos.: use they relate to parts of the international application that do not comply with the prescribed requirements to such tent that no meaningful international search can be carried out, specifically:
3. Claim becaus	s Nes.: se they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(2).
	vations where unity of invention is lacking (Continuation of Item 2 of first sheet)
	al Searching Authority found multiple inventions in this international application, as follows:
See next s	
1. As all r	equired additional search fees were timely paid by the applicant, this international search report covers all
2. X Asalise of any a	archable claims could be searched without effort justifying an additional fee, this Authority did not invite payment dditional fee.
3. As only covers o	some of the required additional search fees were timely paid by the applicant, this international search report nly those claims for which fees were paid, specifically claims Nos.:
4. No requi	red additional search fees were timely paid by the applicant. Consequently, this international search report is to the invention first mentioned in the claims; it is covered by claims Nos.:
Remark on Prote	S. The additional control of
	The additional search lees were accompanied by the applicant's protest.
	No protest accompanied the payment of additional search fees.

Form PCT/ISA/210 (continuation of first sheet (1)) (July 1992)

International application No. PCT/IB 97/00457

- Claims 1-16, 18-22 define a compensator comprising a retardation foil, a retardation foil and a liquid display device.
- II. Claim 17 defines a retardation foil.
- III. Claim 23 defines a method of manufacturing a retardation foil.

Since there is no technical relationship among these inventions involving one ore more of the same or corresponding special technical feature, as defined in Rule 13.2, the claims are considered to represent three different inventive concepts, and do therefore not comply with the requirements of unity of invention.

Form PCT/ISA/210 (extra sheet) (July 1992) .

INTERNATIONAL SEARCH REPORT Information on patent family members

01/10/97

International application No. PCT/IB 97/00457

Patent document cited in search report			Publication date		Patent family member(s)	Publication date
US	5237438	A	17/08/93	EP JP JP JP JP	0512459 A 4330416 A 4330417 A 5019251 A 5061037 A 5061038 A	11/11/92 18/11/92 18/11/92 29/01/93 12/03/93 12/03/93
P	0678567	A1	25/10/95	JP US	8005839 A 5601884 A	12/01/96 11/02/97
JS	5359443	A	25/10/94	EP JP JP	0543678 A 5142509 A 5142510 A	26/05/93 11/06/93 11/06/93
IS	4984874	A	15/01/91	EP JP	0350075 A 2124527 A	10/01/90 11/05/90